

COPEPlus UV MB 10:1

PSC UV MB 10:1 is highly loaded, UV concentrate designed to be used in polyester based engineering grade resins like Hytrel, Keyflex.

Thermal properties:	Value	Test Method
Melting Temperature @ Peak	150-175 ⁰ C	ISO 11357-1/-3

Other properties:	Value	Test Method
Density	1.12+/-0.05	ISO 1183

Delivery form: pellets

Packaging: 50lbs Al/foiled bags

Processing: Designed to be added to the Hytrel, Keyflex types resins using gravimetric feeders during molding, extrusion at 20:1 LDR

PSC UV MB 10:1 does not required drying if used right from the sealed bags, otherwise drying is necessary. Recommended drying conditions: 100⁰C for 3 hours. Desired moisture content <0.08%