

FR MB 68-37

PSC FR MB 68-37 is highly loaded, FR Masterbatch based on PP carrier. Designed to be used between 20:1 to 5:1 LDR. FR MB 68-37 formulated to decrease the amount of the die-drool.

Thermal properties:	Value	Test Method
Melting Temperature @ Peak	105-120°C	ISO 11357-1/-3

Other properties:	Value	Test Method
Density	1.18-1.24+/-0.04	ISO 1183

Delivery form: pellets

Packaging: 55lbs bags, 1,600 lbs Gaylords

Processing: Designed to be added to the PP resin using gravimetric feeders during molding, extrusion.

PSC FR MB 68-37 does not require drying.